

EVERBUILD WIDE JOINT GROUT

DESCRIPTION

EVERBUILD WIDE JOINT GROUT is a grey, fast setting, water resistant cement based floor and wall tile grout with added PVA to promote greater adhesion and flexibility.

BENEFITS

- Excellent water resistance.
- Fills joints up to 15mm
- Fast setting - quicker clean up.
- Compressible.
- Resists mould growth.
- Interior/exterior use.

AREAS FOR USE

- Grouting floor and wall tiles on most surfaces up to 15mm in joint width.
- Recommended for grouting domestic, communal and power shower areas.
- Suitable for constant immersion; eg in swimming pool walls
- Suitable for use with ceramic, quarry and natural stone tiles and mosaics.
- Coloured grouts may be made by adding up to 5% by weight of EVERBUILD POWDER MORTAR TONE.

LIMITATIONS

- Allow adhesive to dry thoroughly before grouting (24hrs on porous, up to 5 days on non-porous surfaces). This prevents staining.
- Never add further water once the grout has been mixed. This will destroy the strength.
- Allow 3 days after grouting before using shower areas.
- Contains coarse silica fillers. May scratch highly glazed and soft tiling. In these circumstances, testing is recommended prior to use.

SURFACES/PREPARATION

Ensure that the area to be grouted is clean, dry and free from loose adhesive before grouting. ALWAYS CHECK THAT THE ADHESIVE IS DRY BEFORE COMMENCING.

TILING SAND/CEMENT RENDER/SCREED/PLASTER/PLASTERBOARD

Mix grout with water as detailed below. Leave at least 24 hours before grouting., except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature.

TILING IMPERVIOUS SURFACES(ASPHALT/EXISTING TILING ETC)

Mix grout with water and leave at least 5 days before grouting, except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature

TILING SURFACES SUBJECT TO MOVEMENT (WOOD ETC)

Mix grout with EVERBUILD SBR diluted 1:1 with water. Leave at least 24 hours before grouting, except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature.

TILING IN AREAS SUBJECT TO INTERMITTENT/CONSTANT WATER IMMERSION

Mix grout with EVERBUILD SBR diluted 1:1 with water. Leave at least 24 hours before grouting., except when using EVERBUILD SBR, where grouting may be carried out 2-4 hours after fixing, depending on temperature. Swimming pools should not be filled for at least three weeks after grouting.

APPLICATION

Always add powder to water. Mix approximately 4 parts by volume powder to 1 part by volume water and mix to a smooth paste. The grout is usable for approximately 1-2 hours at 20°C. Allow to stand for 15 mins then work well into joints using a squeegee. Remove excess grout as you proceed. Allow approximately 15 minutes drying time after grouting before removing excess with a damp cloth. Polish the tiles with a clean, dry cloth when the grout is sufficiently hard. May be walked on after approximately 3 hours. When used externally, do not apply when rain is imminent and protect from rain for at least 5 hours. **Never** add further water once the grout is mixed. This will destroy the bond strength.

SPECIFIC DATA

Appearance:	Fine grey powder										
S.G (20°C):	1.8 gcm ³ (approx).										
Application Temp.	5°C to 35°C.										
Service Temp:	-30 to 100°C.										
Open time/Pot life	30-40 mins @20°C										
Setting time	3 - 4 hours (hard in 24 hours)										
Thickness:	up to 15mm (minimum 3mm)										
Storage:	Store at moderate temperatures. PROTECT FROM DAMP										
COVERAGE TILE SIZE 200 x 100 x 9mm 6mm 150 x 150 x 9mm 6mm 150 x 150 x 9mm 3mm 200 x 100 x 9mm 3mm	<table><tr><th>JOINT WIDTH</th><th>REQ. AMOUNT (kg/m²)</th></tr><tr><td></td><td>1.4</td></tr><tr><td></td><td>1.2</td></tr><tr><td></td><td>0.6</td></tr><tr><td></td><td>0.7</td></tr></table>	JOINT WIDTH	REQ. AMOUNT (kg/m ²)		1.4		1.2		0.6		0.7
JOINT WIDTH	REQ. AMOUNT (kg/m ²)										
	1.4										
	1.2										
	0.6										
	0.7										

HEALTH AND SAFETY

IRRITANT! Contains Portland Cement. Risk of serious damage to eyes .Contact with wet or dry product may cause irritation, dermatitis or burns. Wear suitable protective clothing. After contact with skin, wash immediately with plenty of cold water. If product enters eyes, wash immediately with plenty of cold water for 10-15 mins and seek medical attention .Keep out of reach of children. Use light dust mask if excessive dust is unavoidable.

STORAGE

Store at moderate temperatures. PROTECT FROM DAMP

SHELF LIFE

Minimum 12 months when stored according to manufacturers instructions.