

**TECH DATA - PIPE THREAD SEAL**

General-purpose medium viscosity anaerobic grade for sealing pipe threads and fastening fittings in pneumatic and hydraulic systems. Medium strength for easy disassembly (175kg/cm<sup>3</sup>). Initial bond strength 5-10 minutes. Full strength 6-10 hours. Pressure rated to 2000-3000psi.

**DIRECTIONS**

SHAKE WELL BEFORE USE. Surfaces must be clean and dry. Apply to one surface and assemble components. Wipe clean excess material. Allow to cure for 5-10 minutes before handling/light use. Full strength obtained in 6 hours.

TEST	RESULT
Viscosity	50000 poise
Breakaway strength	175Kg/cm <sup>2</sup>
Attrition	200Kg/cm <sup>2</sup>
Tensile	2000-3000psi
Shear strength	2000-3000 psi
Fixture time	5-10 mins
Full strength	6-10hours
Temp resistance	-40 - +150°C.

<b>EVERBUILD PIPE THREAD SEAL</b> Contains: methyl methacrylate		
 <b>IRRITANT</b>	 <b>HIGHLY FLAMMABLE</b>	Highly flammable. May cause sensitisation by skin contact. Keep out of the reach of children. Do not breathe vapour. Keep container in a well-ventilated place. Keep away from sources of ignition - No smoking. Avoid contact with skin. Wear suitable gloves. If swallowed, seek medical advice immediately and show this container or label.
<b>Everbuild Building Products Ltd</b> Site 41, Knowsthorpe Way, Cross Green Industrial Estate, Leeds LS9 0SW Tel: 0113 240 3456 Fax: 0113 240 0024		

NOTE: Anaerobic adhesives cure when oxygen is excluded hence this pack is much larger than the product contents to provide oxygen to keep the product in its wet state.

As the manufacturer cannot know all the uses its products may be put to, it is the user's responsibility to determine suitability of use. If in doubt, contact Technical Services Department for advice

(*EVERBUILD LOGO*)

**EVERBUILD Building Products Ltd**

Site 41, Knowsthorpe Way, Cross Green Industrial Estate, Leeds LS9 0SW

Tel: 0113 240 3456

Fax: 0113 240 0024

**50ml e      Rev. 1**

Bar Code: 5 029347 60171-