



TECH DATA - THREADLOCK GP

A medium strength, self curing, anaerobic adhesive for locking threads on most nuts, bolts and screws which may need to be disassembled. Examples include hydraulic system bolts, gearboxes, countersunk screws and most construction equipment. Gap filling to 0.25mm. Can be used on "as received" and oil contaminated threads/nuts. Colour red.

DIRECTIONS

SHAKE WELL BEFORE USE. Surfaces must be clean (will tolerate a light oily film) and dry. Apply to both surfaces and assemble components. Wipe clean excess material. Allow to cure for 5-10 minutes before handling/light use. Full strength obtained in 6-10 hours.

EVERBUILD THREADLOCK GP Contains: methyl methacrylate		
 IRRITANT	 HIGHLY FLAMMABLE	Highly flammable. May cause sensitisation by skin contact. Keep out of the reach of children. Do not breathe vapour. Keep container in a well-ventilated place. Keep away from sources of ignition - No smoking. Avoid contact with skin. Wear suitable gloves. If swallowed, seek medical advice immediately and show this container or label.
Everbuild Building Products Ltd Site 41, Knowsthorpe Way, Cross Green Industrial Estate, Leeds LS9 0SW Tel: 0113 240 3456 Fax: 0113 240 0024		

TEST	RESULT
Viscosity	15,000 poise
Breakaway strength	195Kg/cm ²
Attrition	215Kg/cm ²
Tensile	2000-3000psi
Shear strength	2000-3000 psi
Fitxure time	5-10 mins
Full strength	6-10hours
Temp resistance	-40 - +150`C.

NOTE: Anaerobic adhesives cure when oxygen is excluded hence this pack is much larger than the product contents to provide oxygen to keep the product in its wet state.

As the manufacturer cannot know all the uses its products may be put to, it is the user's responsibility to determine suitability of use. If in doubt, contact Technical Services Department for advice

(EVERBUILD LOGO)

EVERBUILD Building Products Ltd

Site 41, Knowsthorpe Way, Cross Green Industrial Estate, Leeds LS9 0SW

Tel: 0113 240 3456

Fax: 0113 240 0024

10g e Rev. 1

Bar Code: 5 029347 60172-